

Torggler

eTics

Paints and coatings

PRIMER VIP

Universal pigmented primer with high filling and masking power, suitable for application of paste coatings on plasters, reinforced skim coats and eTics systems.



- High filling and masking power
- Suitable for eTics systems

APPLICATION AREAS

- Unpainted walls
- Walls painted with tempera paints
- Walls painted with washable water-based paints

WARNINGS

- Environment and substrate conditions: room temperature: min. +5°C / max. +35°C; relative humidity of the environment: < 80%; substrate temperature: min. +5°C / max. +35°C; substrate moisture < 10 of R.H.
- Keep the can tightly closed and protected from frost.
- Safety information for the user is contained in the relevant safety data sheet
- Empty containers or those with slight traces of dried residual product film must be disposed of according to local regulations

INSTRUCTIONS FOR USE

Product dilution and preparation

Dilute with 5 – 10% water by volume. Mix thoroughly. Application tools: Brush, wool roller.

SUBSTRATE PREPARATION

Unpainted wall surfaces If the substrates are not particularly absorbent, apply 1 or 2 coats of Primer VIP directly.

Wall surfaces painted with tempera paints.

If the surface is not particularly crumble, clean the surface thoroughly, fill in any imperfections with putty, smooth with sandpaper and remove dust. Apply 1 or 2 coats of VIP Primer directly. In the case of particularly crumble tempera paints, remove the film, apply 1 coat of acrylic fixative and after 6/12 hours proceed with the application of 1 or 2 coats of Primer VIP.

Wall surfaces painted with washable water-based paints

Thoroughly clean the surface, fill in any imperfections with putty, smooth with sandpaper and remove dust. Then directly apply 1 or 2 coats of Primer VIP.

Application

Apply Primer VIP with brush or wool roller.

Tools cleaning

Clean the tools with water immediately after use.

Rainwater resistance

The product completes the drying and curing process within 8÷10 days under optimal environmental conditions (15÷35°C; R.H. max. 75%). If the product, during this period of time undergoes runoff from rainwater, it could result in unsightly drippings with a translucent and sticky appearance. This phenomenon, which is temporary in nature, does not affect the quality characteristics of the product and can be easily eliminated by hydro-washing or by waiting for the next rainy event.

Safety precautions

- Keep the can tightly closed and frost-free;
- Safety information for the user is contained in the relevant safety data sheet;
- Empty containers or containers with slight traces of dried residual product film must be disposed of according to local regulations;

TECHNICAL SPECIFICATIONS

PARAMETER AND METHOD	MAIN DATA AT 20°C AND 60 % R.H.
Appearance and finish	Opaque
Theoretical yield per coat (ISO 7254)	5 ÷ 6 m ² /l depending on the absorption of the substrate
Dry to the touch	Max 1 h
Dry in depth	Max 24 h
Overpaintable	4 ÷ 6 h
Bulk density (ISO 2811-1)	ca. 1,47 g/ml
Viscosity Brookfield (ASTM D 2196)	ca. 4000 cps
Recommended dry thickness (ASTM D 1186)	30÷50 Micron per hand
Flash point (UNI 8909)	Non flammable
Storage life (UNI 10154)	Min. 24 Months
Binder	Acrylate styrene
Color	Coloured, White

Packaging size	14 l
Pallet	33 buckets

CERTIFICATIONS

VOC classification (Directive 2004/42/EC): Fixing primers. EU VOC limit value for eTics Primer VIP (cat. A/h): 30 g/L (2010). eTics Primer VIP contains a maximum of 30 g/L VOC.

The information contained in this document is reported on the basis of our experience and knowledge; therefore, any recommendations and suggestions made are without any guarantee and must be verified before using the product by those who intend to use it, who assume all responsibility that may result from its use since the conditions of use are not under our direct control. In case of doubt, it is always advisable to make preliminary tests and/or ask for the intervention of our technicians. Torggler reserves the right to modify, replace and/or delete the items, as well as to change the product data in this document without prior notice; in this case the indications given here may no longer be valid. Always refer to the latest version of the data sheet, available at www.torggler.com. Version 01.08.2022.